

DESCRIPTION

Total thickness	ASTM F386-02	inch	0.08
	EN 428	mm	2.00
Wearlayer thickness	ASTM F410-02	inch	0.046
	EN 429	mm	1.16
Backing	ASTM 1303-04	-	-
Weight	-	lbs/sq.ft.	0.53
	EN 430	g/sq.m	2610
Width	-	feet - inch	6'6"
	EN 426	cm	200
Length	-	feet - inch	66'
	EN 426	m	20
Coverage / roll	-	sq.ft.	430.56
	-	sq.m	40

CLASSIFICATION

Reference specification	ASTM F1303-04	-	Type I Grade 1
Fire rating	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	-

PERFORMANCES

Bacteriostatic & fungistatic	-	-	Sanosol®
Surface treatment / maintenance	-	-	SparClean®
Abrasion	ASTM F510-04	mg	1.4
Wear resistance	EN 660.2	mm ³	≤ 2
Coefficient of friction	ASTM D2047-04	-	1
	ASTM C1028-96	-	0.69
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10
Slip resistance – ramp test	EN 13845 (annex C)	class	ESb
Static load (175 psi)	ASTM F970-00	inch	0.004
Dimensional stability	-	-	Excellent
Impact insulation class	ASTM E989-06	-	46
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Chemical & stain resistance	ASTM F925-02	-	Excellent Test results available upon request

ENVIRONMENT

Certification	-	-	Floorscore™
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100