

**DESCRIPTION**

Backing			NT
Thickness	ISO 24 346	mm	2.25 ± 0.15
Weight	ISO 23 997	kg/m <sup>2</sup>	2.20 ± 0.15
Roll width		cm	200 (-0 +1)
Roll length		lm	24

**PERFORMANCE**

Dimensional stability	ISO 23 999 ASTM D 1204	%	≤ 0.3
Abrasion resistance	TABER ISO 9352	mg	≤ 300
Slip resistance	EN 16165 annex B (DIN 51130)		R10
Indentation test	ISO 24 343-1	mm	average ≈ 0.09
Low temperature resistance	D 42 1235 A	°C	- 20
Phonic insulation	ISO 717/2	dB	ΔI = 5
Colour resistance	ISO 105 B02 ISO 4582/80 ASTM D 4459		≥ 7
Fire resistance	ISO 3795/76	mm/mn	0
	FMVSS 302		Conform
	ASTM E648	W/cm <sup>2</sup>	(CRF) > 0.50
	R118		Conform
Resistance to chemicals	ISO 26 987	-	Unaffected by diluted acids and bases Unaffected by domestic products (excluding solvents for plasticized PVC)