

This report has been issued as a replacement of Report No. 15117.2 to correct a typographical error in the product name.





Accredited for compliance with ISO/IEC 17025 -

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration

OIL-WET INCLINING PLATFORM SLIP RESISTANCE TEST

Nera Wood sheet vinyl

Prepared for: Gerflor Australasia Pty Ltd

Steve Gradecak 17 Cato Street

HAWTHORN EAST VIC 3123

Specimen Description: Nera Wood sheet vinyl, 500x1000 mm.

No. of Specimens: 1 off

Surface Structure: Smooth

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Specimen Configuration: Fixed

Test Direction: Test conducted parallel with surface profile.

Joint Type & Width: N/A
Air Temperature: 21°C

Test Standard: AS 4586:2013 Slip resistance classification of new pedestrian surface

materials, Appendix D - Oil Wet Inclining Platform Test

Test Shoe: Leipzig V73-SP

Test Location: ATTAR, Unit 1, 64 Bridge Road, Keysborough.

Test Date: 14 February 2020

Test Personnel: Awel Guled and Dale Siegle

Displacement Space	Not tested	
(rounded to the nearest 0.5cm ³ /dm ²):		
Displacement Space Assessment Group	Not tested	
(Appendix E, AS 4586 - 2013):	Not tested	
Corrected mean overall acceptance angle (α_{ave})	10°	
(rounded down to the nearest degree):	10	
Classification:	R10	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Dale Siegle

Compliance and Test Technician

Approved Signatory

Awel Guled

Reviewed By:

Compliance and Test Technician

Approved Signatory




Figure 1: Nera Wood sheet vinyl
Arrow indicates direction of testing



CLASSIFICATION CRITERIA – AS 4586 - 2013 Oil Wet Inclining Platform Test – Appendix D

Compliance

TABLE 5: CLASSIFICATION OF PEDESTRIANSURFACE MATERIALS ACCORDINGTO THE OIL-WET INCLINING PLATFORM TEST

Classification	Angle, degrees
No Classification	<6
R9	≥6 <10
R10	≥10 <19
R11	≥19 <27
R12	≥27 <35
R13	≥35