

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

17 Cato Str	tralasia Pty Ltd eet ast VIC 3123		Test Numb Issue Date Print Date	er : : :	20-00536 13/11/202 13/11/202	20	
Sample Description	Vinyl sports flooring Colour : Blue End Use : Flooring Nominal Composition : He Nominal Mass per Unit Area/I	rformance 9mm" eterogeneous PVC Density : 5400g/n nm	12				
S ISO 9239.1-2003	Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source						
	Date of Sample Arrival		21/10/2020				
	Date Tested	12/11/2020					
	CHF Value	1	2	3	Mean		
	Non Directional	4.3	4.5	4.5	4.4	kW/m²	
	Smoke Value	1	2	3	Mean		
	Smoke Value Non Directional	1 599		3 589	Mean 590	%.min	
		-		-		%.min	
	Non Directional	-		-		%.min	
	Non Directional Observations :	-		-	590	%.min	

220521

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

47361

Accredited for compliance with ISO/IEC 17025 - Testing

Page 1 of 2

HAFL A. JACKSON B.Sc.(Hons)



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

۰۱ م ~

APPROVED SIGNATORY

(C)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Gerflor Australasia Pty Ltd
	17 Cato Street
	Hawthorn East VIC 3123

20-005367 Test Number : Issue Date 13/11/2020 13/11/2020 **Print Date** :

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

220521

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

47361

Accredited for compliance with ISO/IEC 17025 - Testing

Page 2 of 2





Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd

APPROVED SIGNATORY

0204/11/06

C