AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : GERFLOR AUSTRALASIA PTY LTD

17 CATO STREET

HAWTHORN EAST VIC 3123

TEST NUMBER : 7-579534-CV ISSUE DATE : 05/07/2011 PRINT DATE : 05/07/2011

SAMPLE DESCRIPTION Clients Ref: "Tarrasafe Super"

Vinyl Flooring

Colour: Grey

Approximate Thickness: 2.2mm

Material Specification:
Nominal Composition: Vinyl
Nominal Total Mass: 2880g/m2
Nominal Backing: N/A

ASISO 9239.1-2003 Reaction to Fire Tests for Floorings
Part 1 Determination of the Burning Behaviour

using a Radiant Heat Source 30/05/2011

Date of sample arrival: 30/05/2011

Date tested: 04/07/2011

Results: CHF (Critical Heat Flux / Critical Radiant Flux)

1 2 3 Mean

Non directional 8.8 8.4 8.8 8.7 kW/m2

Smoke Value

Non directional 178 136 188 167 %.min

Observations: Melting
Blistering

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2 degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was adhered to substrate of 6mm thick fibre reinforced cement board using Roberts 12 vinyl adhesive and clamped prior to testing.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

188197 1 (END OF REPORT) PAGE 1

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
-Chemical Testing of Textiles & Related Products : Accreditation No. 983
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if ammended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

MICHAEL A. JACKSON B.Sc.(Hons)

LIMITED

APPROVED SIGNATORY

0204/11/06