




| DESCRIPTION  |                  |                    |   |
|--|------------------|--------------------|---|
| Total thickness  | EN ISO 24346     | mm                 | 2.00  |
|  | ASTM F386-02     | inch               | 0.08  |
| Wearlayer thickness  | EN ISO 24340     | mm                 | 0.70  |
|  | ASTM F410-02     | inch               | 0.028   |
| Weight   | EN ISO 23997     | g/sq.m             | 2635  |
| Width of sheet   | EN ISO 24341     | cm                 | 200   |
|  | -                | feet - inch        | 6'6"  |
| Length of sheet  | EN ISO 24341     | lm                 | 25  |
|  | -                | feet - inch        | 82'   |
| CLASSIFICATION   |                  |                    |   |
| Norm / Product specification   | -                | -                  | EN ISO 10582  |
| European classification  | EN ISO 10874     | class              | 34 - 43   |
| Fire rating  | EN 13 501-1      | class              | Br-s1   |
| Static electrical propensity   | EN 1815          | kV                 | < 2   |
| Slip resistance wet : ramp test with oil   | EN 16165 app B   | class              | R10   |
| PERFORMANCE  |                  |                    |   |
| Wear resistance  | EN 660.2         | mm <sup>3</sup>    | ≤ 2.0   |
| Wear group   | -                | group              | T   |
| Type binder content  | ISO 10582        | Type               | I   |
| Dimensional stability  | EN ISO 23999     | %                  | ≤ 0.40  |
| Dimensional stability (average value measured)                                     | -                | %                  | 0.08  |
| Residual indentation (requirement)   | EN ISO 24343-1   | mm                 | ≤ 0.10  |
| Residual indentation (average value measured)                                      | -                | mm                 | ≈ 0.03  |
| Impact sound insulation  | EN ISO 717-2     | dB                 | 8   |
| Castor chair test (type W)   | ISO 4918         | -                  | OK  |
| Thermal conductivity   | EN ISO 10456     | W/(m.K)            | 0.25  |
| Colour fastness  | EN ISO 105 - B02 | degree             | ≥ 6   |
| Surface treatment  | -                | -                  | Protecsol® 2  |
| Chemical products resistance   | EN ISO 26987     | -                  | OK  |
| Anti-bacterial activity (E. coli - S. aureus – MRSA) (1)                           | ISO 22196        | -                  | > 99 % Inhibits growth  |
| Antiviral activity (human coronavirus 229E) (1)                                    | ISO 21702        | -                  | 99.7% after 2h  |
| ENVIRONMENT / INDOOR AIR QUALITY   |                  |                    |   |
| TVOC after 28 days   | ISO 16000-6      | µg/ m <sup>3</sup> | < 10  |
| Certification  | -                | -                  | Floorscore®   |
| CE MARKING   |                  |                    |   |
|  | EN 14041         | -                  |  |
|  |                  | -                  |  |

(1) The implementation of an effective cleaning regime is the best defence against infection