

DESCRIPTION

Total thickness	EN ISO 24346	mm	2.25
Wearlayer thickness	EN ISO 24340	mm	0.70
Weight	EN ISO 23997	g/sqm	2815
Width of sheet	EN ISO 24341	cm	200 - 400
Length of sheet	EN ISO 24341	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance (1)	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10






PERFORMANCES

Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	-	group	T
Type binder content	EN 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (measure)	-	mm	≈ 0.05
Impact sound insulation	EN ISO 717-2	dB	≈ 6
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance (2)	EN ISO 26987	-	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/m ³	< 100
--------------------	-------------	-------------------	-------

CE MARKING

	<p>EN 14041</p>	  
		

(1) Regarding the resistance to chemicals, please download the corresponding leaflet from our website.