




DESCRIPTION			
Total thickness	EN ISO 24346	mm	3.35
Wearlayer thickness	EN ISO 24340	mm	0.55
Weight	EN ISO 23997	g/sqm	2400
Width of sheet	EN ISO 24341	cm	200 /400
Length of sheet	EN ISO 24341	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN 651
European classification	EN ISO 10874	class	33-42
Fire rating	EN 13 501-1	class	Bfl-S1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	< 2.0
Wear group	-	group	T
Dimensional stability (requirement)	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.20
Impact sound insulation	EN ISO 717-2	dB	19
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance (1)	EN ISO 26987	-	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/m ³	< 100
CE MARKING			
	<p>EN 14041</p>		
			

(1) Regarding the resistance to chemicals, please download the corresponding leaflet from our website.
Updated : 24 11 2021