

DESCRIPTION

| | | | |
|-----------------|--------------|------------------|------|
| Total thickness | EN ISO 24346 | mm | 2.00 |
| Weight | EN ISO 23997 | g/m ² | 3300 |
| Width of sheet | EN ISO 24341 | cm | 200 |
| Length of sheet | EN ISO 24341 | lm | 20 |

CLASSIFICATION

| | | | |
|------------------------------|--------------|-------|--------------|
| Norm / Product specification | - | - | EN ISO 10581 |
| European classification | EN ISO 10874 | class | 34 - 43 |
| Fire rating | EN 13 501-1 | class | Bfl-s1 |
| Static electrical propensity | EN 1815 | kV | < 2 |




PERFORMANCE

| | | | |
|------------------------------|------------------|---------|-------------|
| Type Binder content | EN ISO 10581 | type | II |
| Dimensional stability | EN ISO 23999 | % | ≤ 0.40 |
| Residual indentation | EN ISO 24343-1 | mm | ~ 0.05 |
| Castor chair test (type W) | ISO 4918 | - | OK |
| Thermal conductivity | EN ISO 10456 | W/(m.K) | 0.25 |
| Colour fastness | EN ISO 105 - B02 | degree | ≥ 6 |
| Surface treatment | - | - | PUR PROTECT |
| Chemical products resistance | EN ISO 26987 | class | OK |

ENVIRONMENT / INDOOR AIR QUALITY

| | | | |
|--------------------|-------------|--------------------|-------------|
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 10 |
| Certification | - | - | Floorscore® |

CE MARKING

| | | | |
|--|----------|--|---|
|  | EN 14041 | |  |
| | | |  |