

### DESCRIPTION

Description		PVC welding rod with bio-based plasticizer for hot welding to ensure a watertight connection between 2 PVC rolls Especially developed for PVC floorcoverings with bio based plasticizer (Symbioz,...)
Installation		Hot welding - for a better weld use an adapted nozzle
Weight	g/lm	17,8 ± 1,0
Shore		72 ± 3 Sh A.
Diameter	mm	4,0 ± 0,2
Packaging	unit/box	1 coil (100 (+4/-0) lm)
Colors available		Consult Gerflor.com
Product Code(s)		0507

### PERFORMANCES

Strength at break- EN ISO 527R	MPa	17,8 ± 1,0
Elongation at break- EN ISO 527R	%	320 ± 50
Melting range- ISO 11357-2	°C	160 - 200