

**DESCRIPTION**

Total Thickness	EN ISO24346	mm	4.25		
Thickness of the wearlayer	EN ISO24340	mm	0.63		
Weight	EN ISO 23997	g/m <sup>2</sup>	3570		
Size	EN ISO 24342	mm	245 x 1250	150 x 750	500 x 500
Number of planks /tiles and sqm per box	-	-	11 / 3.37 m <sup>2</sup>	31 / 3.49 m <sup>2</sup>	15 / 3.75 m <sup>2</sup>

**CLASSIFICATION**

Norm/Product Specification	-	-	EN ISO 11638		
<b>European classification</b>	<b>EN ISO 10874</b>	<b>classe</b>	<b>33/42</b>		
Fire rating	EN 13 501-1	classe	Bfl-s1		
Static Electrical Propensity	EN 1815	kV	< 2		
Slip Resistance Wet	DIN 51130	classe	R10		





**PERFORMANCES**

Wear Resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0		
Wear Group	QB 30	groupe	T		
<b>Impact Sound Insulation</b>	<b>EN ISO 717-2</b>	<b>dB</b>	<b>20</b>		
<b>Room Impact</b>	<b>NFS 31 074</b>	<b>dB</b>	<b>&lt; 65</b>		
Dimensional Stability (norm)	EN ISO 23999	%	≤ 0.25		
Dimensional Stability (average measure)	EN ISO 23999	%	≤ 0.03		
Residual Indentation (norm)	EN ISO 24343-1	mm	≤ 0.20		
Residual Indentation (average measure)	EN ISO 24343-1	mm	0.12		
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25		
Colour Fastness	EN 20 105 - B02	degré	≥ 6		
Chemical Products Resistance	EN ISO 26987	classe	OK		
Surface Treatment	-	-	ProtecShield™		

**ENVIRONMENT / INDOOR AIR QUALITY**

TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10		
--------------------	-------------	--------------------	------	--	--

**MARQUAGE CE**

	EN 14041	-	  
		-	