




<b>DESCRIPTION</b>			
Total thickness	EN ISO 24346	mm	2.00
Wearlayer thickness	EN ISO 24340	mm	0.70
Weight	EN ISO 23997	g/sq.m	2635
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	25
<b>CLASSIFICATION</b>			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	≤2
Slip resistance wet : ramp test with oil	DIN EN 16165 annex B (DIN 51130)	class	R10
<b>PERFORMANCE</b>			
Wear resistance	EN 660-2	mm <sup>3</sup>	≤ 2.0
Wear group	-	group	T
Type binder content	ISO 10582	Type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105-B02	degree	≥ 6
Surface treatment	-	-	Protecsol® 2
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E. coli - S. aureus) (1)	ISO 22196	-	> 99 % Inhibits growth
Antiviral activity (human coronavirus 229E) (1)	ISO 21702	-	99.7% after 2h
<b>ENVIRONMENT / INDOOR AIR QUALITY</b>			
Certification	-	-	Floorscore®
<b>CE MARKING</b>			
	EN 14041	-	
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection