

DESCRIPTION

Total thickness on grain side	EN ISO 24346	mm	2.00
Wear layer thickness	EN ISO 24340	mm	0.85
Weight	EN ISO 23997	g/m ²	2350
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	≤2
Slip resistance wet: ramp test with oil	DIN EN 16165 annex B (DIN 51130)	class	R11
Slip resistance wet : bare foot	DIN EN 16165 annex A (DIN 51097)	class	B
Slip resistance - ramp test	EN 13845-C	class	Esf-Esb






PERFORMANCE

Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation	EN ISO 24343-1	mm	≤ 0.10
Castor chair test	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105-B02	degree	≥6
Chemical products resistance	EN ISO 26987	-	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	   
---	----------	---	---