

DESCRIPTION					
Total Thickness	EN ISO 24346	mm	6,00		
Thickness of the wearlayer	EN ISO 24340	mm	0,70		
Weight	EN ISO 23997	g/m ²	9850		
Size	EN ISO 24342	mm	214 x 1239	242 x 1461	391 x 729
Number of planks /tiles and sqm per box	-	-	6 / 1.59 m ²	5 / 1.77 m ²	5 / 1.43 m ²
CLASSIFICATION					
Norm/Product Specification	-	-	EN ISO 10582		
European Classification	EN ISO 10874	class	34 - 43		
Fire Rating	EN 13 501-1	class	Bfl-s1		
Static Electrical Propensity	EN 1815	kV	≤2		
Slip Resistance Wet	DIN EN 16165 annex B(DIN 51130)	class	R10		
PERFORMANCES					
Wear Resistance	EN 660-2	mm ³	≤2.0		
Wear Group	-	group	T		
Type Binder content	ISO 10582	group	I		
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15		
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10		
Castor chair test	ISO 4918	-	OK		
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25		
Colour Fastness	EN ISO 105-B02	degree	≥ 6		
Surface Treatment	-	-	PUR+ MATT		
Chemical Products Resistance	EN ISO 26987		OK		
ENVIRONMENT / INDOOR AIR QUALITY					
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10		
CE MARKING					
CE	EN 14041				
					