







	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
	<b>PRODUCT DESCRIPTION</b>			
Surface treatment	-	-	-	
Surface complex	-	-	-	
Foam	-	-	-	
Thickness	EN ISO 24346	-	mm	2
Weight	EN ISO 23997	-	kg/m <sup>2</sup>	2.9
Length	EN ISO 24341	-	lm	26.5 max
Width	EN ISO 24341	-	lm	1.5
	<b>SPORT PROPERTIES</b>			
Shock absorption	EN 14808	≥ 25	%	-
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
	<b>TECHNICAL CHARACTERISTICS</b>			
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
Impact sound insulation	EN ISO 717-2	-	dB	3
	<b>CLASSIFICATION</b>			
Fire	EN 13501-1	-	-	
Anti-bacterial activity (E. coli - S. aureus - MRSA) (1)	ISO 22196	-	-	> 99 % inhibits growth
	<b>DECLARATION OF PERFORMANCE</b>			
	DOP-005-1002-A	-	-	Fire Sliding Coefficient Abrasion Resistance Rolling Load Resistance
	<b>INSTALLATION METHODS</b>			
	<b>Gerflor's recommendation</b>		<b>Unit</b>	<b>Results</b>
Glued installation: "Original"	Level of dampness of the subfloor		%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)

(1) The implementation of an effective cleaning method is the best defence against infection