





	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
	PRODUCT DESCRIPTION			
Surface treatment	-	-	-	
Surface complex	-	-	-	
Foam	-	-	-	
Thickness	EN ISO 24346	-	mm	9 mm
Weight	EN ISO 23997	-	kg/m ²	5.4
Length	EN ISO 24341	-	lm	26.5 max
Width	EN ISO 24341	-	lm	1.5
Surface compact layer thickness	-	-	mm	2
	SPORT PROPERTIES			
Shock absorption	EN 14808	≥ 35	%	P2
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 3
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Impact Protection Index	AC-P90-205	-	%	82
	TECHNICAL CHARACTERISTICS			
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
Impact sound insulation	EN ISO 717-2	-	dB	20
	CLASSIFICATION			
Fire	EN 13501-1	-	-	Cfl,s1
Anti-bacterial activity (E. coli - S. aureus - MRSA) (1)	ISO 22196	-	-	> 99% inhibits growth
	DECLARATION OF PERFORMANCE			
	DOP-005-1016-A	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Rolling Load Resistance
	INSTALLATION METHODS			
	Gerflor's recommendation		Unit	Results
Glued installation: "Original"	Level of dampness of the subfloor		%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolsport: "Flexible"			%	RH < 92% (BS 8203) or < 7.0% humidity (CCM)
Dry-Tex™ System			%	No limit (no dripping water on the slab)

(1) The implementation of an effective cleaning method is the best defence against infection